

TECHNICAL DATA SHEET

FANCY

Specifications

2017.07.25

GRADE : FA-U093

APPLICATION :

CUSTOMER :

Lot No : Sample

PHYSICAL PROPERTIES	TEST METHOD		UNITS	SPEC
Basis Weight	Total	ISO 536	g/m ²	93 (±10%)
Thickness	Total	ISO 534	mm	0.55 (±15%)
Initial Efficiency (Model : TSI-8130)	0.3 μ m NaCl (5.3cm/sec)	US 42 CFR part 84 or EN 143	%	Over 99.95
Initial Pressure (Model : TSI-8130)	(5.3cm/sec)	US 42 CFR part 84 or EN 143	Pa	Below 38
Flame Retardant Rating	Total	UL94	-	HF-1

CHECKED BY

APPROVED BY

HongKong Office : Fancy Creation Industrial (HK) Ltd.

TEL : +852-2881 6601, FAX : +852-2881 8629

CHINA SuZhou Factory: No.1002, Chunshen Road, Huangdai , Suzhou. CHINA

TEL : +86-512-6638 7321, FAX : +86-512-6638 2893